

Washi Torinoko

GPWT

ILFORD GALERIE Washi Torinoko is a fine art paper with a traditional, Washi, Japanese base and a fine textured surface. The base, exclusively produced for ILFORD, is manufactured using a specialized Japanese Tanmo machine which produces a paper so refined it looks like it has been handmade. The Washi base is made in the Echizen area of Japan. This area is famous for the production of traditional Japanese paper and has the history of 1500 years in paper production. Torinoko Washi has the unique ILFORD inkjet coating that gives the final print a wide colour gamut and excellent colour consistency. The paper has a fine textured surface, is acid free with no optical brighteners and so is suitable for fine art reproduction.

FEATURES

- Look feel of a traditional washi paper
- Fine texture
- Free of optical brighteners

PRINTER & INK COMPATIBILITY

Designed for use with both desktop and wide format inkjet printer systems using either aqueous dye or pigment inks from major manufacturers.

PHYSICAL PROPERTIES

Weight	110gsm	
Opacity	>90%	
Caliper	170 Micron (6,7 mil)	
Tint	97,2 -0,3 3,6	
OBA Content	No	
Acid Free	Yes	

HANDLING TIPS

Finished prints should be interleaved and stored carefully to prevent scratching. FineArt paper prints are typically more delicate than conventional resin coated (RC) papers such as Pearl, Glossy, Lustre surfaces and should be handled with additional care. Before printing please check that there are no loose paper fibres or debris on the media surface as this may lead to print errors. As with any FineArt media using raw paper it is possible that some debris may exist.

ILFORD have taken great care to ensure that in general our papers are free from loose paper fibres, but please check before you make the final print. Cotton gloves are recommended to avoid contaminants getting onto the surface.

STORAGE

It is recommended that you store your paper in the original product packaging/boxes. Products must be stored in a cool, dry environment away from direct sunlight. Optimal storage and Operating conditions are 15–25°C, 35–65% relative humidity, non-condensing.

AVAILABILITY

Available in sheets and rolls. For more details please see the product page on www.ilford.com.